

Technical data sheet

DEMIDEKK Terrace glaze

Product description

Type

High quality, water-based oil based on alkyd oil.



Special features and benefits

With just one coat, the oil provides good top protection and a lasting color (service intervals up to three years). Efficiently protects the wood against moisture and cracks as well as against graying and weathering caused by UV rays. It contains agents that protect against algae and mold growth. Has highly penetrating and water-repellent properties. Can protect against moisture already one hour after application. In the drying times section, you can see when the substrate can be fully loaded again.

Recommended scope

Recommended on terrace floors, privacy fences, garden furniture etc.

underground

Recommended for use on substrates where a matt transparent appearance is desired.



product data

packaging sizes	0.75 L (capacity 0.68 L), 3 L (capacity 2.7 L) and 10 L (capacity 9 L)
shades	According to color sample.
generic type	Alkyd Emulsion.
solid volume	21 ± 2 Volume%
Specific Gravity pH	1 6.5 to 8.5
VOC for ready to use mixture	EU limit value for this product (product category A/e): 130 g/l. This product contains max. 60 g/l VOC.

Technical data sheet**DEMIDEKK Terrace glaze****Application Data**

Contents of cans with different production numbers should be mixed. Stir well. Lasur penetrates less deeply into knots than into more absorbent areas. Gives an iridescent effect but may result in reduced durability in areas of lower penetration. Application on less absorbent substrates such as larch can be the poorer penetration lead to reduced durability.

application process

Spread or roll and spread. The product is not suitable for spray application.

Cleaning the painting tools

Water and **JOTUN Penselrens**.

dilution

The product is a finished product and should not be diluted.

Coverage (per coat) and layer thickness

**yield per
Coating
(m²/litre)**

Recommended: 6 – 10

Comments: The product should penetrate the wood and only form a light film on the surface.

conditions during application

Do not apply in direct sunlight, damp weather and low temperatures. Low temperatures in spring and autumn can lead to dew formation and thus to dull spots in the paint.


Please note the weather forecast.

drying times

High humidity and low temperatures increase the drying time.

The drying time was measured with the given values:

Relative Humidity (RH) 50% 50%	50 %		
air temperature	23 °C	15 °C	10 °C
underground temperature	23 °C	15 °C	10 °C
Dust dry	3 Std.	5 Std.	8 Std.
Dry (fully resilient)	8 Std.	12 Std.	16 Std.



Technical data sheet

DEMIDEKK Terrace glaze



Processing instructions

The substrate must be stable, clean and dry.

underground	Treatment
New, impregnated wood:	<p>Leave to dry for 1-2 months. Carefully remove deposits of copper salt (verdigris) with a brush. Clean carefully with water (with a garden hose) and leave to dry.</p> <p>Decklack: DEMIDEKK Terrasslasyr. When the substrate is dry apply only a thin coat. Apply product over the entire length and on up to two boards at the same time. Remove excess with a lint-free cloth. The product should penetrate the wood and only form a light film on the surface.</p> <p>In order to achieve an even result, it is recommended to work in the adjacent areas.</p>
Old, impregnated wood:	<p>Must be pre-treated with DEMIDEKK Terrassfix according to the processing instructions . Please note! Remaining DEMIDEKK Terrassfix must be rinsed off thoroughly with clean water. Sand greyed wood down to the intact wood grain.</p> <p>Decklack: DEMIDEKK Terrasslasyr. When the substrate is dry apply only a thin coat. Apply product over the entire length and on up to two boards at the same time. Remove excess with a lint-free cloth. The product should penetrate the wood and only form a light film on the surface.</p> <p>In order to achieve an even result, it is recommended to work in the adjacent areas.</p>
Untreated, oiled or glazed wood:	<p>Must be pre-treated with DEMIDEKK Terrassfix according to the processing instructions . Please note! Remaining DEMIDEKK Terrassfix must be rinsed off thoroughly with clean water.</p> <p>Decklack: DEMIDEKK Terrasslasyr. When the substrate is dry apply only a thin coat. Apply product over the entire length and on up to two boards at the same time. Remove excess with a lint-free cloth. The product should penetrate the wood and only form a light film on the surface.</p> <p>In order to achieve an even result, it is recommended to work in the adjacent areas.</p>

maintenance

Clean floorboards annually with **JOTUN 3-i-1 Kraftvask og Træ- og Murrens** (removes dirt and refreshes colour).

storage

During storage or transport, store/transport the containers upright and frost-free.

waste disposal

Liquid paint must not be allowed to enter the sewage system or bodies of water. Dispose of liquid paint at an approved local recycling center or paint and varnish collection point.

Technical data sheet**DEMIDEKK Terrace glaze****health and safety**

Please note the environmental and precautionary measures on the container.

A safety data sheet has been issued for the product.

Detailed information on health and safety hazards and precautions to be taken when using this product is provided in the Material Safety Data Sheets.

First aid measures, see point 4.

Operation and storage, see section 7.

See Section 14 for transport information .

See Section 15 for regulatory information .

Contact information

Jotun (Germany) GmbH
Haferweg 38
22769 Hamburg

Tel: +49 40 85 19 60

info@jotun.de
jotun.decorative.de@jotun.com http://
www.jotun.de

Disclaimer

The information in this document is given to the best of Jotun's knowledge based on laboratory tests and practical experience. Jotun's products are considered semi-finished goods and as such are often processed under conditions beyond Jotun's control. Jotun cannot guarantee anything other than the quality of the product itself. Minor product adjustments can be made to meet local requirements. Jotun reserves the right to change the given data without notice.

Processors should always consult Jotun for specific advice on the general suitability of the product for their purposes and specific application practices.

In the event of any discrepancies between different language editions of this document, the English (Eng) version shall prevail.